

DATASHEET FPM-D 80 SH-A FOOD BROWN

Fluoro Rubber

PROPERTIES	DIN STANDARD	UNIT	VALUE	UNIT	VALUE
Colour			BROWN		BROWN
Hardness 23°C	DIN ISO 868	Shore A	80 ± 5	Shore A	80 ± 5
Hardness 23°C/3 sek	DIN ISO 868	Shore A	77 ± 5	Shore A	77 ± 5
Modulus 100%	DIN 53 504	MPa	≥6	psi	≥ 870
Tensile strength	DIN 53 504	Mpa	≥8	psi	≥ 1660
Elongation at break	DIN 53 504	%	≥ 150	%	≥ 150
Tear strenght	DIN ISO 34-1	kN/m		lbf/inch	
spec. gravity	ISO 1183	kg/m ³	2400	g/cm ³	2,4
Rebound elasticity	DIN 53 512	%	7	%	7
Résistance à l'abrasion	DIN 53516	mm ³	220	mm ³	220
Compression set 70°C/24h	DIN ISO 815-1	%	≤7	%	≤7
Compression set 100°C/24h	DIN ISO 815-1	%	≤9	%	≤9
Compression set 150°C/24h	DIN ISO 815-1		≤14		≤14
Service température min.		°C	-20	°F	-4
Service température max.		°C	+220	°F	+428

FOODSTUFF APPROVAL



All the above data comes from random tests on current production, based on a standard sample according to ISO, DIN and ASTM. These standards cannot be applied directly to the building element.

Our technical advice, whether oral, written or test-based, is provided to the best of our knowledge, but should be considered non-binding. They do not dispense from testing the product to verify its suitability for the process and intended purpose.

The use and processing of the products is beyond our control and under your responsibility.

In case of liability, this will be limited to the value of the product delivered and used.

We guarantee the irreproachable quality of our products in accordance with our general conditions of sale and delivery.